



GC A-40

pelletized activated carbon

GC A-40 is a virgin activated carbon. Derived from bituminous coal, it is pelletized in form. Its superior activity and surface area make it ideal for most vapor phase applications. The uniformity of its shape makes it particularly attractive in applications where low-pressure drop is a consideration.

Specifications

Particle Size - (Diameter), mm:	4.0
(Length), mm:	6.0
Mean Particle Diameter, mm:	4.7
CCl ₄ Activity, %:	70 (min)
Iodine No., mg/g:	1050 (min)
Surface Area, m ² /g:	1050 (min)
Hardness, %:	95 (min)
Moisture, % (as packaged):	3 (max)
Typical Density, lbs./cu.ft.:	28-31
g/cc:	0.44-0.50

*Standard packaging is in 55 lb. vinyl bags. Other packaging is available upon request.

Caution!

Wet activated carbon removes oxygen from air causing a severe hazard to workers inside carbon vessels. Confined space/low oxygen procedures should be put in place before any entry is made. Such procedures should comply with all applicable Local, State and Federal guidelines.