



## **GC D-40**

pelletized activated carbon

**GC D-40** is a virgin activated carbon. Derived from bituminous coal, it is pelletized in form. Its size and the uniformity of its shape make it particularly attractive in applications where low-pressure drop is a consideration.

### **Specifications**

Particle Size (Diameter), mm:	4.0
(Length), mm:	6.0
Mean Particle Diameter, mm:	4.7
CCl <sub>4</sub> Activity, %:	50 (min)
Iodine No., mg/g:	800 (min)
Surface Area, m <sup>2</sup> /g:	800 (min)
Hardness, %:	95 (min)
Moisture, % (as packaged):	5.0 (max)
Typical Density, lbs./cu.ft.:	24-28
g/cc:	0.38-0.44

\*Standard packaging is in 200 lb. fiber drums. Other packaging is available upon request.

### **Caution!**

*Wet activated carbon removes oxygen from air causing a severe hazard to workers inside carbon vessels. Confined space/low oxygen procedures should be put in place before any entry is made. Such procedures should comply with all applicable Local, State and Federal guidelines.*